
**EssenSeal®** 



Preparation phase

Shake the bottle before use to aerate the powder.




Powder

Fill a level spoonful with powder.

On a smooth glass mixing block, place 1 level dosing spoon of powder and 1 drop of liquid. A reminder of the ideal mixing ratio is placed on the vials.

Caution: Hold the bottle upside down and wait until a single drop falls onto the mixing plate.





immediately after use.

extemporaneously by gradually incorporating the powder into the liquid. The mixture should have a smooth and shiny appearance. Consistency should be creamy.



Treatment in process •••••



Apply the sealer to the canal walls using a root filler, gutta-percha points or any other device suitable for this purpose. The choice of filling technique is left entirely to the practitioner.



The working time at temperatures below 25°C is more than 30 minutes. The setting time in the mouth (37°C and > 95 % relative humidity) is less than 3 hours.

Note: Heat and humidity are known to accelerate the setting of the cement.

Check the quality of the filling by radiographic inspection. In case of re-treatment, use conventional chemo-mechanical filling removal techniques.

